

ROKESTER 3610

CHEMICAL NAME	Polyester polyol
TECHNICAL REQUIREMENTS	Appearance at 25°C viscous liquid (visually) Hydroxyl value, mg KOH/g335 – 365 (PN-EN ISO 2554:2001) Acid value, mg KOH/g1.0 – 2.0 (PN-EN ISO 2114:2005, solvent: acetone) Water, % (m/m) max. 0.15 (PN-ISO 760:2001) Dynamic viscosity at 25°C, mPas 2000 – 4000 (PN-EN ISO 3219:2000, cone No.4, rpm 180)
GENERAL DATA	Density at 25°C, g/ml ~1.24 Flash point, °C.....above 150
APPLICATION	Aromatic polyester polyol designed for use in PUR/PIR foams.