

# ROKOLUB 50-B-10

## TECHNICAL PRODUCT SPECIFICATION

**NUMBER** **TDS: KR/451/01**

**DATE** 30.08.2022.

**CHEMICAL NAME** Butanol, propoxylated and ethoxylated.

<b>TECHNICAL REQUIREMENTS</b>	Appearance at 25°C .....	Homogeneous liquid, colourless to yellow
	Acid value, mg KOH/g .....	max. 0.1 (ASTM D7253-16, bromothymol blue)
	Water content, % (m/m).....	max. 0.08 (ASTM D4672-18)
	Kinematic viscosity at 40°C, mm <sup>2</sup> /s.....	9 – 11 (ASTM D445-19)
	Kinematic viscosity at 100°C, mm <sup>2</sup> /s.....	2 – 4 (ASTM D445-19)

<b>INFORMATIVE DATA*</b>	ISO VG .....	32
	Molecular weight, g/mol.....	~450
	Viscosity index.....	~180
	Pour point, °C.....	<(-40)
	Flash point, °C.....	>180
	Functionality .....	~1
	Density at temperature. 20°C, g/mL.....	1.02
	Contains BHT free antioxidant.	

\* These informative data are not technical requirements and cannot form the basis for any claims.

**USE**

Rokolub 50-B-10 is a product with a high Viscosity Index, soluble in water in 20°C, and can be used as synthetic PAG base oil for the formulation of high performance lubricants.

**Applications:**

Industrial bearing and compressor lubricant. Component for metalworking fluids and functional fluids for forming metals. It can be used as base stock for hydraulic fluids.

The performance advantages offered by PAG based lubricants can be summarized as follows:

- High Viscosity Index,
- Superior lubricity – reduced wear characteristics and good Extreme Pressure performance,
- Provide a high level of thermal conductivity,
- Offer the safety features of a high flash point and biodegradable condensate.

**PACKAGING**

Tank wagons or tanker trucks made of stainless steel, plastic containers with a capacity of 1 m<sup>3</sup>, steel or plastic drums with a capacity of 200 dm<sup>3</sup> and other packaging as agreed with the customer

**STORAGE**

Store in tightly closed containers, keep away from humidity. Avoid direct sunlight. Maximum storage temperature +40°C. Recommended usage temperature 20-25°C. Viscosity increases as temperature decreases

**SHELF LIFE**

Guaranteed period of stability: 12 months from the date of manufacture. After the expiry of this period, the product can be used upon verifying the conformity of its parameters with performance requirements.

**TRANSPORTATION**

This product is not regulated for carriage according to ADR/RID, IMDG, ICAO/IATA

**CLASSIFICATION AND LABELLING**

This technical specification is applicable only if accompanied by the Safety Data Sheet in force. Pursuant to statutory requirements, only the Safety Data Sheet includes updated safety information.

The information contained herein is provided in good faith, based on our state of the art knowledge and experience. We reserve the right to amend this Technical Specification as a result of technological progress and product development by the manufacturer.

This product is intended for the purposes specified herein, for industrial and professional use. To use the product for purposes other than indicated herein, please contact PCC Rokita for consultation sending an e-mail to: [rokopol@pcc.eu](mailto:rokopol@pcc.eu).

We cannot assume any liability for the use and application of our products, technical assistance and information provided (whether verbal, written or by way of product evaluations), including any suggested formulations and recommendations.

Therefore, it is imperative that you test our products, technical assistance and information provided to determine to your own satisfaction whether they are suitable for your needs, production, your intended uses and applications. Such analysis adopted to the conditions of the use and application should include at least application tests, technical feasibility of the suggested solutions, taking into account safety requirements, health and environmental issues.

Unless otherwise specified in writing, our products are offered under our applicable Standard Terms and Conditions of Sale available on our website. Any information, including technical assistance, is provided without warrant and can change at any time without notice. The parties explicitly agree that the Customer accepts and explicitly releases us from any liability in tort, contract or otherwise, for any loss or damage arising from the use of our products, information or technical assistance. Any declarations and recommendations other than stated herein are not valid or binding. Nothing in this document is intended to be a recommendation to use any product in violation of patent claims concerning material of intended use.